



FXHD88-31 无溶剂环氧地坪封闭底漆

FXHD88-31 Solvent-free epoxy floor seal primer

产品简介 Product introduction	<p>采用进口 828 树脂或 128 树脂, 优质溶剂、BYK 助剂、特殊附着力促进剂、美国气体固化剂等原材料, 通过先进的技术工艺精制而成。是一种强附着力、低粘度的双组份地坪底涂材料。产品包括组分 A (主剂) 和组分 B (固化剂)。</p> <p>This product is made of imported 828 resin or 128 resin, high-quality solvent, BYK assistant, special adhesion promoter, American gas curing agent and other raw materials by advanced technology. It is a two-component floor primer with strong adhesion and low viscosity. This product includes component A (main agent) and component B (curing agent)</p>
适用范围 Application	<p>没有特殊要求的正常或疏松混凝土、金刚砂、水磨石等各种需要施工环氧涂料的基面。</p> <p>Various substrates that require epoxy coatings without special requirements, such as Normal or loose concrete, emery, terrazzo etc.</p>
产品性能 Product performance	<p>对混凝土基面有良好的渗透力和高度的封闭性, 加强基面硬度并提供优良的附着力。通用型环氧底漆采用了改性树脂加入特殊工序处理, 同时兼顾了渗透性和封闭性两种性能。</p> <p>This product has good permeability and high sealing to the concrete base, strengthens the base hardness and provides excellent adhesion. By adding the modified resin into the special process, the product performance takes both permeability and sealing into account.</p>
产品外观 Appearance	<p>组分 A (主剂) 为无色透明液体、组分 B (固化剂) 为淡黄色透明液体</p> <p>Component A (Main agent) is transparent liquid, Component B (Curing agent) is light yellow transparent liquid</p>
混合比率 Mixing ratio	<p>双组分: 主剂 / 固化剂= 17 / 3 (重量比)</p> <p>Two components: Main agent / Curing agent=17 / 3 by weight</p>
包装规格 Package	<p>双组份包装 (25L): 25L 一组, 组份 A 为 20 L 铁桶 (17KG), 组份 B 为 5 L 铁桶 (3KG)</p> <p>Two-component packaging (25L): 25L contains Component A 20L bucket (17KG) and Component B 5L bucket (3KG).</p>
粘度 (CPS/25°C) Viscosity (CPS/25°C)	<p>主剂: 100-200; 固化剂: 50-100</p> <p>Base: 100-200; hardener: 50-100</p>
使用环境 Construction environment	<p>35°C ≧ 温度 ≧ 5°C、湿度 ≧ 80%</p> <p>35°C ≧ Temperature ≧ 5°C、humidity ≧ 80%</p>
涂装膜厚 Film thickness	<p>干膜: 20μm/道 湿膜: 40μm/道</p> <p>Dry film thickness: 20μm/ coat Wet film thickness: 40μm /coat</p>
静置时间 Standing time	<p>10-15 minutes</p>
施工适用期 Pot life	<p>30 minutes</p>



涂装配套 Coating system	适用上涂：无溶剂型环氧中涂漆 FXHD88-32 Subsequent coat: Solvent Free Epoxy intermediate paint FXHD88-32
涂覆率 Coverage rate	理论值：0.15-0.2kg/m ² Theoretical: 0.15-0.2kg/m ² 实际值：与表面处理，外界环境，施工方法等多种因素有关。 Actual: depending on the surface treatment and environment conditions, and application methods.
干燥时间 (湿度 65%/25℃) Drying time (humidity 65%/25℃)	温度(Temperature): 25 °C 指触干燥 (Dry to touch): 4-6hrs 实干(Dry to handle): 20-24hrs
储存期限 Shelf life	半年 6 months
使用说明 Using method	1、施工前请向本公司确认施工工艺 Please confirm the construction process with our company before construction 2、严禁混入其它油漆，必须严格按照规定比例加入固化剂。 It is forbidden to mix other paints, and the curing agent must be added in strict accordance with the specified proportion. 3、涂装场所地表温度低于 5 °C 或高于 35 °C，相对湿度大于 80%，应避免施工。 When the surface temperature of the coating site is lower than 5 °C or higher than 35 °C, and the relative humidity is higher than 80%, construction shall be avoided. 4、涂装场所应严禁烟火，洁净无尘、通风良好，若通风不良，需用相关设备强制通风。 No fireworks shall be allowed in the construction site, and it shall be kept clean, dust-free and well ventilated. In case of poor ventilation, forced ventilation shall be required.
提醒注意 Declaration	本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。 The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.