

## FX-0210F 氟碳各色面漆

## **FX-0210 Fluorocarbon Finishes**

产品特性 Characteristics  产品用途 Uses	极佳的防腐性能、极好的耐候性; Excellent corrosion and weather resistance 极好的耐油性和耐水性; Excellent oil and water resistance 极好的耐冲击和耐磨损性能; Excellent resistance to impact and abrasion 良好的施工性能。 Good workability  广泛用于桥梁、高速公路护栏、高档建筑、石油设备及储罐的防腐。 As anticorrosive finish widely for bridge, highway guardrail, high-grade building, petroleum					
	equipment and storage tank					
颜 色 Color	各色 All colors					
施 工 条 件 Application methods	无气喷涂       推荐         airless spray       recommended         喷嘴尺寸       0.5~0.6mm         nozzle tip       0.5~0.6mm         压力       150kg/cm²         nozzle pressure       150kg/cm²         稀释比率       0~5% by weight (重量比)         thinning ratio       0~5% (by weight)         适用于无气喷涂、空气喷涂、刷涂及辊涂					
	May be applied by spray, brush, or roller.					
稀释剂 Thinner	氟碳稀释剂 Fluorocarbon thinner					
混合比率 Mixing ratio	双组分: 主剂/固化剂=10/1(重量比) Two component: base/curing agent=10/1 by weight					
混合使用期 Pot life	温 度 ( $\mathbb{C}$ ): $5\mathbb{C}$ $20\mathbb{C}$ $30\mathbb{C}$ Temperature 混合使用期 (hrs): $8$ $6$ $5$ Pot life					
涂 装 膜 厚 Film thickness	干膜: 30μm/道 Dry film thickness:30μm/coat					
固体含量 Solid content	60%					
比重 Specific gravity	1.15					
涂 覆 率 Spreading rate	理论值: 0.09kg/m²/30μm 0.078L/m²/30μm 0.078L/m2/30μm 0.078L/m2/30μm					
	实际值: 与表面处理, 外界环境, 施工方法等多种因素有关。 Practical: varies depending on the surface treatment, environment and application method					
干燥时间 Drying time	温度( $^{\circ}$ C) 5 20 30 Temperature ( $^{\circ}$ C) $1.5$ 0.7 0.5 dry to touch (hrs)					



	实干: (hrs) Through dry (hrs)	6	4	3			
	Timough dry (ms)						
涂装间隔	Min. 最小(hrs)	24	20	10			
Coating interval	Min.(hrs) Max. 最大(hrs)	_	_	_			
	Max(hrs)						
储存期限	一年						
Shelf life	12 months						
包装规格	双组份包装: 22kg 为一组,组份一为 20kg,组份二为 2kg						
package	2K packaging: A kit 22kg contains Part A 20kg and Part B 2kg.						
	底漆表面应清洁干燥,无污物。						
表面处理							
Surface preparation	注意施工与底漆的涂装间隔。						
	Please pay attention to the coating	g ınterval.					
适用底材      氟碳底漆及多种底漆和中层漆配套或参考我公司的配套。							
Preferable substrate	Compatible with fluorocarbon primer or other primers and intermediate coats, or refer to our coating						
	system.						
安全注意事项	任何油漆施工中均应保证提供以下措施:						
Safety Precautions	The following shall be guaranteed during any paint applications:						
	避免接触皮肤和眼睛。						
	Avoid skin and eye contact.						
	如果油漆接触到皮肤或眼睛,应用大量水冲洗并立即就医。						
	In case of skin or eye contact, flush with large amount of water and immediately get medical						
	attention.						
	保证良好的通风。						
	Assure well-ventilated working place.						
	小心火灾或爆炸。						
	Take precautions of the risks of fire or explosion.						
	现场遵守一切健康安全规定。						
	Observe all health and safety reg						
提醒注意	本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控						
Declaration	制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发						
	展,此中所有信息均以我方确认为准。						
	The information given on this technical data sheet is correct to the best of our knowledge. In						
	consideration of the application conditions of the product are beyond our control, so no guarantee is						
	involved herein, namely, we are responsible for the buyers only in terms of their selecting a product.						
	All data must be clarified from our company because of the constantly improvement of our product						
	and its manufacturing process.						