



GH-750 湿固化环氧煤沥青防腐漆

GH-750 Moisture Cure Epoxy Coal Tar Anticorrosive Primer

产品特性 Characteristics	当空气湿度达 94% 时，仍能正常固化成膜，且物理和化学性能不变 A normal cured film and unaffected physical chemical performance can be obtained when R.H. reaching 94%. 干燥快、与喷砂处理后的钢材、表面附着力极好 Quick dry; excellent adhesion to sand blasted steel surfaces. 耐磨性、耐冲击性优良 Good abrasion and impact resistance. 涂装间隔短，可气割性和可焊接性优异 Short coating interval; excellent gas cutting and welding property.			
产品用途 Uses	主要用于船底部、集装箱外、底部，各种地下管道，钢铁产品地下防腐蚀用漆。 Mainly used as anticorrosive coatings on the iron and steel surfaces of ship bottoms, outside and bottom of containers and underground pipelines.			
颜色 Color	黑色、棕色 Black, brown			
施工条件 Application conditions	无气喷涂 Airless spray	喷嘴尺寸 Nozzle size	压力 Pressure	稀释比率 Dilution ratio
	推荐 Recommended	0.8~0.9mm	100~150kg/cm ²	0~5%by weight (重量比)
	适用于常规的喷涂、刷涂和辊涂		May be applied by spray, brush or roller.	
稀释剂 Thinner	FXH-4 环氧稀释剂 Epoxy Thinner			
混合比率 Mixing ratio	双组分：主剂/固化剂=10/1 (重量比) Two components: base/hardener=10:1 by weight			
混合使用期 Pot life	温度： Temperature	10℃	20℃	30℃
	混合使用期： Pot life	10hrs	8hrs	6hrs
涂装膜厚 Film thickness	干膜： Dry film thickness:	125μm/道	湿膜： wet film thickness:	233μm/道 233μm/ coat
固体含量 Solid content	72%			
比重 Specific gravity	1.46			



涂覆率 Coverage rate	理论值 : 0.28 千克/平方米/125 μ m 0.192L/平方米/125 μ m Theoretical: 0.28kg/m ² /125 μ m 0.192L/m ² /125 μ m 实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment, application methods.
干燥时间 Drying time	温度 10 $^{\circ}$ C 20 $^{\circ}$ C 30 $^{\circ}$ C Temperature 指触干燥 2.5hrs 2hrs 1.5hrs Dry to touch 实干: 18hrs 12hrs 10hrs Dry to handle:
涂装间隔 Coating interval	Min. 最小 18hrs 12hrs 10hrs Max. 最大 — — —
储存期限 Shelf life	一年 12 months
包装规格 package	双组份包装: 27.5kg 为一组, 组份一为 25kg, 组份二为 2.5kg 2K packaging: A kit 27.5kg contains Part A 25kg and Part B 2.5kg.
表面处理 Surface treatment	底材温度在-10 $^{\circ}$ C以上, 可继续施工 Application can be performed when the substrate is above -10 $^{\circ}$ C. 用清水冲去盐分以及其它水溶性污物。 Remove salts and other water soluble contaminants with fresh water. 依照 SSPC-SP1 溶剂清洗标准除去油脂。 Remove oil in accordance with the solvent cleaning standard SSPC-SP1. 用高压空气吹扫除去灰尘等污物。 Remove the contaminants like dust with high pressure blower. 施工前确认表面彻底清洁、干燥、无结露。 Confirm the surface clean, dry and free of dew prior to application.
涂装配套 Coating system	适用下涂: 环氧煤沥青底漆 Applicable preceding coat: Epoxy Coal Tar Primer 如有任何疑问请向津海公司查询。 If any question, please refer to Jinhai Paints.
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site
提醒注意	本说明书所提供信息均为目前我方所掌握最全面正确的资料, 鉴于产品使用条件非我方所能控



Declaration

制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.
